

Acoustic processes in materials

Leonid V. Zhigilei and Henry Helvajian, Guest Editors

The coupling of acoustic energy with materials structures and processes is at the core of such current and emerging application areas as ultrasound-enabled materials characterization, structuring, and processing. High concentration of acoustic energy, such as upon the collapse of a cavitation bubble, has been shown to provide conditions for the synthesis of unusual material phases and structures, while intriguing reports on acoustic activation of surface diffusion, desorption, and catalysis hold high promise for applications where heating must be avoided or rapid switching of surface conditions is required. Some of the recent scientific and technical advances in the general area of acoustically enabled materials synthesis, processing, and characterization are reviewed in this issue of *MRS Bulletin*. Additional discussion of experimental data and computational results providing insights into the fundamental mechanisms and channels of the acoustic energy coupling to atomic-scale surface features and adsorbates is also provided in this article.

Introduction

The generation and probing of acoustic waves of different types, such as bulk longitudinal or transverse/shear waves and surface/Rayleigh waves, are used in many well-established applications, including nondestructive testing and material characterization,¹ signal processing,² dry laser cleaning,³ chemical sensing,⁴ and manipulation of fluid flow in microfluidics devices.⁵ New opportunities that could expand the range of acoustically enabled applications are emerging from exploratory studies that report the ability of acoustic energy to drive rearrangement of crystal defects,^{6,7} induce crystallization in amorphous materials and thin films,^{8,9} and affect atomic rearrangements^{10,11} and chemical reactions^{12–15} on surfaces. “Traditional” application areas, such as nondestructive detection/evaluation of material heterogeneities and defects, are also experiencing a revival due to the development of new techniques that enable *in situ* monitoring of subsurface microstructure evolution with high temporal and spatial resolutions, as well as advanced approaches that take advantage of nonlinear acoustic effects to achieve a dramatic boost in the structural sensitivity and spatial resolution of acoustic microscopy. Many of these new developments have the potential for making a strong impact on acoustically assisted material processing and *in situ/in operando* material characterization.

The articles in this issue of *MRS Bulletin* are focused on some of the most promising and intriguing developments in

the area of acoustically enabled materials synthesis, processing, and characterization, which are likely to be of interest to a broad expanse within the materials R&D communities.

Advanced methods of acoustic materials characterization

Recent improvements in the sensitivity and spatial resolution of acoustic nondestructive evaluation methods are largely achieved through utilization of nonlinear acoustic effects, as discussed in the article by Zaitsev¹⁶ in this issue. Starting from a brief overview of conventional linear acoustic diagnostic techniques (pulse-echo, resonance-based methods), the article proceeds with a broad overview of different types of nonlinear acoustic response and provides examples of the manifestation of nonlinear effects in acoustic probing of heterogeneous materials that exhibit a structure-induced “mesoscopic” acoustic nonlinearity. The applications of nonlinear acoustic probing range from characterization of nanoscale heterogeneities, such as dislocation structures, to identification of microcracks and granular materials, to macroscopic nondestructive testing of engineering structures, and to seismic studies performed at a scale of kilometers.

Among the many methods for the generation of acoustic waves, photoacoustic techniques stand out for their noncontact nature and flexibility, enabling creative design of experimental setups tuned to practical application needs. An example of

Leonid V. Zhigilei, Department of Materials Science and Engineering, University of Virginia, USA; lz2n@virginia.edu
Henry Helvajian, Physical Sciences Laboratories, The Aerospace Corporation, USA; henry.helvajian@aero.org
doi:10.1557/mrs.2019.103

a photoacoustic technique that targets *in situ* characterization of the evolving subsurface microstructure in samples exposed to high levels of radiation damage is provided in the article by Hofmann et al. in this issue.¹⁷ They present the laser-induced transient grating spectroscopy technique where the optical generation and probing of surface acoustic waves (SAWs) is used for analysis of microstructure evolution on the sub-microsecond time scale and with tunable depth resolution.

Materials synthesis in a cavitation bubble

While the acoustic waves in the applications discussed so far serve as the agency for nondestructive probing, a high concentration of acoustic energy can also result in material modification, damage, or even synthesis of new phases and nanomaterials. In particular, the collapse of an optically or acoustically generated bubble within a liquid can create pressure and temperature conditions that are amenable to chemical synthesis (so-called “sonochemistry”)^{18,19} or a significant modification of the material confined within the collapsing bubble via both chemical and physical phenomena.²⁰ The Barcikowski et al. article²¹ in this issue brings together four experts in complementary research areas—nanoparticle synthesis by laser ablation in liquids, time-resolved probing of laser-induced phase transformations in colloidal nanoparticles, acoustic cavitation and sonochemistry, and laser-induced bubble dynamics. It provides a comprehensive and authoritative overview of the complex and multifaceted cavitation phenomenon that to a large extent controls the material synthesis in ultrasonic sonochemistry and laser ablation in liquids.

Acoustic activation of surface processes

In general, acoustic waves are not expected to directly affect atomic or molecular-level surface processes, such as diffusion, desorption, or chemical reactions. The large frequency mismatch between acoustic waves (typically ≤ 100 MHz) and vibrational states of surface species (on the order of THz) seemingly excludes the possibility of dynamic coupling of acoustic waves to surface processes. The periodic perturbations of the surface energy landscape associated with acoustic strain are generally small and should also have negligible effect on surface mobility or binding energy of an adsorbate. Surprisingly, however, there has been a steady growth in experimental evidence of the ability of surface and bulk acoustic waves interacting with surfaces to substantially enhance the rates and selectivity of heterogeneous catalytic reactions,^{12–15} desorb molecules, atoms, and ions,^{22–28} and facilitate surface diffusion of atomic clusters.^{10,11}


These results are reviewed in two articles in this issue of *MRS Bulletin*. The article by Inoue²⁹ is focused on the effects of acoustic waves on chemisorption and surface reactions, which are shown to be sensitive not only to the nature of the acoustic activation (bulk versus

surface waves), but also to the crystallographic surface orientation. The large magnitude of acoustic enhancement of chemical reactions, demonstrated under properly chosen experimental conditions, suggests that the acoustic stimulus can be effective in promoting heterogeneous catalysis. The article by Ma et al.³⁰ provides compelling experimental evidence of acoustically induced ejection/desorption of atoms, molecules, and particles from a thin layer of solid sample deposited on a surface of a metal foil that is irradiated from the back side by a high-energy pulsed laser beam. Possible mechanisms responsible for the ejection of molecules are discussed and the advantages of this method for “cold” desorption of heat-sensitive organic molecules in the context of mass spectrometry are demonstrated.

Mechanisms of the acoustic activation of surface processes

Despite the intriguing nature and potential practical importance of the experimental observations of the enhancement of surface catalysis, diffusion, and desorption by acoustic waves, reliable theoretical interpretation of these results is currently lacking. In the case of ejection from a continuous micrometer-thick molecular layer deposited on a metal foil, used in the laser-induced acoustic desorption setup discussed in the article by Ma et al.³⁰ in this issue, the ejection process may be driven by the direct dynamic interaction of the laser-induced stress wave with the sample layer, in a manner similar to dry laser cleaning³ or the laser-induced forward-transfer technique used for controlled material deposition.³¹

For individual atoms, molecules, and small clusters, such as the ones shown in **Figure 1**, however, the large frequency mismatch between the surface species and acoustic waves calls into question the contribution of the dynamic resonant coupling of the energy of an acoustic wave to surface vibrational states. The absence of an obvious explanation of the experimentally observed acoustic activation of surface processes gives rise to a range of (largely speculative) hypotheses. Some of those are based on the presumed presence of mesoscopic-scale substructures/domains¹³ that can effectively couple to a long-wavelength acoustic excitation or nanoscale



stressed surface features that can release the stored strain energy in response to an acoustic activation, thus providing extra energy needed for the desorption of molecules.²⁶ Others suggest that acoustically induced variation of the spatial distribution of adsorbates may affect the surface reaction rates.¹⁴

Modification of binding energies and diffusion barriers of adsorbed species induced by the surface strain^{32–35} has also been considered as a mechanism that may be responsible for the acoustic activation of surface processes.¹⁴ Indeed, a detailed theoretical and computational analysis performed for linear (sinusoidal) elastic SAWs³⁶ suggests that a combined effect of the transient modification of the diffusion barriers and adiabatic temperature variation due to the periodic oscillations of the acoustic strain can lead to a noticeable enhancement of adatom surface diffusion for large strain magnitudes and systems that exhibit strong strain dependence of the diffusion barriers. Moreover, theoretical analysis³⁷ suggests that structuring of surface adatoms in the presence of standing SAWs can also be achieved, thus suggesting an attractive route for acoustic control of surface self-assembly without permanent modification of the substrate. The large surface strains ($\sim 10^{-2}$) required for reaching practically relevant levels of the diffusion enhancement and the strong quadratic scaling of the diffusion enhancement with the strain amplitude in the absence of nonlinear enrichment of the SAW spectrum by higher harmonics, however, make the assumption of the linear SAW propagation questionable and suggest that nonlinear effects should be considered.

The role of nonlinear effects

The notion of the relevance of nonlinear effects (see the article by Zaitsev¹⁶ in this issue) to the acoustic activation of surface processes is supported by a joint experimental-computational study of surface diffusion of small atomic clusters,¹¹ where a dramatic diffusion enhancement by SAWs was observed experimentally, as illustrated by the plots of the mean square displacement (MSD) of Au₈ clusters moving on a (111) silicon substrate with and without SAWs (Figure 2). The slope of the MSD versus time dependence is proportional to the surface diffusion coefficient, and the data shown in Figure 2 demonstrate a 19-fold increase in the cluster mobility in the presence of laser-generated SAWs. The results of large-scale molecular dynamics simulations¹¹ clearly link the diffusion enhancement to the nonlinear sharpening of the wave profiles³⁸ (Figure 2c), which can be described in terms of the generation of high frequency harmonics (Figure 2d) that effectively couple to the vibrational modes of the clusters (the cluster resonance frequency is marked by the green arrow in Figure 2d).

Indeed, as can be seen from the changes in the cluster diffusion coefficient with time of SAW propagation (Figure 2b), the diffusion coefficient remains low initially, when the wave profile is close to a sine function. Starting from around 1500 τ (τ is a unit of time used in the simulation¹¹), however, the diffusion coefficient rapidly increases and reaches a maximum value that is more than 4500 \times higher than the value of thermal

diffusion at the temperature of the substrate. This enhancement of surface diffusion corresponds to an equivalent increase of the substrate temperature by a factor of about 3.7. The plots of the wave profiles shown in Figure 2c demonstrate that the large mobility enhancement coincides with sharpening of the SAW profile and generation of a shock front. During the subsequent propagation of the SAW, the wave amplitude and the shock front sharpness decrease due to the strong dissipation near the wave front, as the high-frequency harmonics associated with the shock formation efficiently couple with thermal phonons. Nevertheless, despite a substantial attenuation of the wave by the time of 6500 τ , and the corresponding decrease of the cluster mobility, the diffusion coefficient remains almost 1000 \times higher than that of the thermally activated diffusion. The direct correlation between the evolution of the high frequency components of the wave spectrum and the diffusion enhancement suggests that the latter can be attributed to the dynamic coupling of high-frequency harmonics with the cluster vibrational modes that facilitates an effective transfer of the acoustic energy to the cluster motion.

The interactions of a nonlinear wave with surface adsorbates, atomistic/mesoscopic heterogeneities, and defects are likely to strongly affect the evolution of the wave itself, thus resulting in a mutual feedback between the acoustic activation of surface processes and the frequency-dependent dissipation/generation of the wave harmonics. In general, the results of the simulations and experiments suggest that the nonlinear sharpening of the acoustic waves may play an important role in the activation of atomic-scale surface processes, and the nonlinear effects should be considered, along with other mechanisms discussed in articles by Inoue²⁹ and Ma et al.³⁰ in this issue, in the interpretation of the highly intriguing, but not yet fully understood experimental evidence of the acoustic enhancement of surface processes.

Concluding remarks

The diversity of the physical and chemical processes that can be activated or enhanced by an acoustic stimulus, as well as a wide range of current and emerging applications already utilizing acoustic waves for materials characterization, synthesis, and modification, discussed in the articles in this issue of *MRS Bulletin*, suggest that the delivery and manipulation of acoustic energy is likely to play an increasingly important role in materials science and engineering. Progress in the incorporation of the acoustic methods into mainstream materials synthesis and processing techniques requires significant advancement in the fundamental understanding of the interaction of acoustic waves with different elements of the material microstructure, particularly in the nonlinear regime, as well as the mechanisms of acoustically induced structural and phase transformations. This progress can only be achieved through stronger interdisciplinary interactions between the materials research community and researchers working in areas as disparate as nonlinear acoustics, cavitation and bubble dynamics, seismology, ultrasonic imaging, and surface chemistry.




Figure 2. Acoustic activation of surface diffusion of small atomic clusters by surface acoustic waves (SAWs) (a) observed experimentally, and (b) predicted in a series of large-scale molecular dynamics simulations. The acoustic activation of surface diffusion is related to the (c) formation of a shock front and (d) generation of high-frequency harmonics capable of direct energy transfer to the clusters adsorbed on the surface. The plot in (a) shows the evolution of mean square displacement (MSD) of individual Au₈ clusters moving on a (111) silicon substrate as a result of thermally activated diffusion (no SAWs, red circles) and SAW-assisted diffusion in regions located 6-mm (blue rhombus) and 12-mm (black squares) from the SAW source. The plot in (b) shows the evolution of the cluster diffusion coefficient with time of SAW propagation, with the equivalent scale of the effective temperature, T_{eff} , which would yield the corresponding diffusion coefficients by thermal activation shown on the right side of the plot. The inset in (b) depicts a schematic representation of the computational system colored by an instantaneous pressure distribution produced by an initial sinusoidal SAW, where the color varies from red (compression) to blue (tension). (c, d) (Left to right) The temporal evolution of the SAW profile and corresponding harmonics in the wave spectrum predicted in the simulations. Lennard-Jones units are used in (b–d).¹¹ Note: D , diffusion coefficient; k_B , the Boltzmann constant; T , temperature of the substrate; ν , frequency; τ , ϵ unit of time; σ , energy and length parameters of Lennard-Jones potential.

Acknowledgments

L.V. Z. acknowledges financial support from the National Science Foundation through Grant No. CMMI-1562929.

References

1. M. Levy, H.E. Bass, R. Stern, Eds., *Modern Acoustical Techniques for the Measurement of Mechanical Properties* (Academic Press, New York, 2001).
2. K.-Y. Hashimoto, *Surface Acoustic Wave Devices in Telecommunications: Modelling and Simulation* (Springer-Verlag, Berlin, 2000).
3. S. Pleasants, N. Arnold, D.M. Kane, *Appl. Phys. A* **79**, 507 (2004).
4. A. Buvailo, Y. Xing, J. Hines, E. Borguet, *Sens. Actuators B* **158**, 444 (2011).
5. L.Y. Yeo, J.R. Friend, *Annu. Rev. Fluid Mech.* **46**, 379 (2014).
6. A. Bakai, N. Lazarev, *Sov. Phys. Solid State* **28**, 1373 (1986).
7. I. Ostrovskii, L. Steblenko, A. Nadtochii, *Semiconductors* **34**, 251 (2000).

8. T. Ichitsubo, E. Matsubara, T. Yamamoto, H.S. Chen, N. Nishiyama, J. Saida, K. Anazawa, *Phys. Rev. Lett.* **95**, 245501 (2005).
9. J.K. Wuenschell, H. Helvajian, *Opt. Express* **27**, 5859 (2019).
10. A.J. Manzo, H. Helvajian, *Proc. SPIE* **8969**, 896908 (2014).
11. M.V. Shugaev, A.J. Manzo, C. Wu, V.Yu. Zaitsev, H. Helvajian, L.V. Zhigilei, *Phys. Rev. B* **91**, 235450 (2015).
12. Y. Inoue, Y. Matsukawa, K. Sato, *J. Am. Chem. Soc.* **111**, 8965 (1989).
13. S. Kelling, T. Mitrelias, Y. Matsumoto, V.P. Ostanin, D.A. King, *J. Chem. Phys.* **107**, 5609 (1997).
14. S.J. Reese, D.H. Hurley, H.W. Rollins, *Ultrason. Sonochem.* **13**, 283 (2006).
15. Y. Inoue, *Surf. Sci. Rep.* **62**, 305 (2007).
16. V.Y. Zaitsev, *MRS Bull.* **44** (5), 350 (2019).
17. F. Hofmann, M.P. Short, C.A. Dennett, *MRS Bull.* **44** (5), 392 (2019).
18. K.S. Suslick, *Science* **247**, 1439 (1990).
19. P. Cintas, G. Cravotto, A. Barge, K. Martina, *Top. Curr. Chem.* **369**, 239 (2015).
20. D. Zhang, B. Gökce, S. Barcikowski, *Chem. Rev.* **117**, 3990 (2017).

21. S. Barcikowski, A. Plech, K. Suslick, A. Vogel, *MRS Bull.* **44** (5), 382 (2019).
22. D.R. Denison, *J. Vac. Sci. Technol.* **6**, 214 (1969).
23. C. Krischer, D. Lichtman, *Phys. Lett. A* **44**, 99 (1973).
24. B. Lindner, U. Seydel, *Anal. Chem.* **57**, 895 (1985).
25. V.V. Golovlev, S.L. Allman, W.R. Garrett, C.H. Chen, *Appl. Phys. Lett.* **71**, 852 (1997).
26. A.V. Zinovev, I.V. Vervoykin, J.F. Moore, M.J. Pellin, *Anal. Chem.* **79**, 8232 (2007).
27. A.M. Dow, A.R. Wittrig, H.I. Kenttämä, *Eur. J. Mass Spectrom.* (Chichester) **18**, 77 (2012).
28. S. Ehlert, A. Walte, R. Zimmermann, *Anal. Chem.* **85**, 11047 (2013).
29. Y. Inoue, *MRS Bull.* **44** (5), 361 (2019).
30. X. Ma, Y. Zhang, H.-R. Lei, H.I. Kenttämä, *MRS Bull.* **44** (5), 372 (2019).
31. P. Serra, A. Piqué, *Adv. Mater. Technol.* **4**, 1800099 (2019).
32. C. Roland, G.H. Gilmer, *Phys. Rev. B* **46**, 13428 (1992).
33. M. Mavrikakis, B. Hammer, J.K. Nørskov, *Phys. Rev. Lett.* **81**, 2819 (1998).
34. A. van de Walle, M. Asta, P.W. Voorhees, *Phys. Rev. B* **67**, 041308 (2003).
35. M.W. Wu, H. Metiu, *J. Chem. Phys.* **113**, 1177 (2000).
36. C. Wu, V.Yu. Zaitsev, L.V. Zhigilei, *J. Phys. Chem. C* **117**, 9252 (2013).
37. C. Wu, V.Yu. Zaitsev, L.V. Zhigilei, *Appl. Phys. Lett.* **103**, 221601 (2013).
38. A. Lomonosov, V.G. Mikhalevich, P. Hess, E.Yu. Knight, M.F. Hamilton, E.A. Zabolotskaya, *J. Acoust. Soc. Am.* **105**, 2093 (1999). □




Leonid V. Zhigilei is a professor of materials science and engineering at the University of Virginia. He studied materials science at Leningrad Polytechnic Institute and earned his PhD degree at Tomsk State University and St. Petersburg State University, Russia. Before joining the faculty of the University of Virginia, he was a postdoctoral researcher in the Department of Chemistry at The Pennsylvania State University. His research interests include multiscale modeling of materials behavior far from equilibrium, mechanisms of phase transformations, nanomaterials, and surface processes. Zhigilei can be reached by email at lz2n@virginia.edu.



Henry Helvajian is a senior scientist at The Aerospace Corporation. He received his BS and MS degrees at Stanford University concentrating on lasers and quantum electronics, and earned his PhD degree at the University of Southern California in photochemistry and gas-phase kinetics/spectroscopy. He was a NAS/NRC post-doctoral researcher in the Chemistry Division at the Naval Research Laboratories prior to joining The Aerospace Corporation. His research interests include laser fabrication of glass-ceramic microelectromechanical systems, manufacturing processes for mass-producing nanosatellites, laser ultrasonic processes in materials synthesis,

altering speed of sound by lasers, and process control for additive manufacturing. Helvajian can be reached by email at henry.helvajian@aero.org.



Journal of MATERIALS RESEARCH

2018 PAPER OF THE YEAR

Congratulations!

Huachen Cui, Ryan Hensleigh, Hongshun Chen and Xiaoyu Zheng

Virginia Tech

“Additive Manufacturing and size-dependent mechanical properties of three-dimensional microarchitected, high-temperature ceramic metamaterials”

Published February 14, 2018 - *JMR* Volume 33, Issue 3

This paper will be freely available to the materials community in perpetuity.

mrs.org/jmr

JANIS

Cryogenic Wafer Probe Stations

- Applications include nano science, materials and spintronics
- 3.2 K - 675 K; high vacuum or UHV
- Up to 8 probes, DC to 67 GHz, plus fiber optics
- Zoom optics with camera and monitor
- Cooling options: liquid helium, liquid nitrogen or cryogen free
- Horizontal, vertical or vector magnetic field options are available

Contact us today:
sales@janis.com
www.janis.com/ProbeStations.aspx
www.facebook.com/JanisResearch